



کیمیا اکسیر آریسا
تأمین کننده مواد اولیه رنگ، رزین، پوشش، مرکب چاپ، ساختمان، چسب و پلاستیک



Kimya Exir ARISA

Supplier of Raw Material in Paint, Resin, Coating, Construction, Adhesive and Plastic

تلفن ۰۲۱۸۸۴۴۶۶۹۹۸ ۰۲۱۸۸۴۳۳۰۷۴ فکس ۰۲۱۸۸۴۳۳۰۷۴

ایمیل kimyaarisa@gmail.com ۰۲۱۸۸۴۴۶۵۹۴ ۰۲۱۸۸۴۲۸۰۳۷

وبسایت www.arisaco.ir تلگرام ۰۹۰۲۸۲۷۴۸۵۹

Curing Agents

Isocyanates

	TS %	NCO %	Solvents	Properties
Curing Agent RF/AE DE	26±1	8 - 8.5	ethylacetate	For solvent based products
Curing Agent D	65±1	19 - 21	toluene	For solvent based products
Curing Agent W3 DIL	70±1	12.5 - 13.5	acetone	For water-based systems
Curing Agent W 10	80±1	13 - 15	propylene carbonate	For water-based systems
Curing Agent W3	100	18 - 19		For water-based systems
Curing Agent CH	100	30 - 32		For solvent based products

Different curing agents

	TS %	Solvents	Properties
PZ-28 Dil. 7,5	7.5±0.50	isopropyl alcohol / isobutyl alcohol	Diluted polyaziridine
Curing Agent WS 5	27.5±1.00	water	Polyurea for water-based systems
Xama 7/60	60±2	diacetone alcohol	Diluted polyaziridine
PZ-28	100		Propylenaziridine for water and solvent systems
Curing Agent X7	100		Ethylenaziridine for water and solvent systems. It works also at room temperature

